

## Description

Inhibited dielectric mineral oil formulated with hydrogenated base oils. Especially recommended for use as an insulation fluid in electrical equipment.

## Properties

- High dielectric strength.
- Excellent cooling properties.
- High oxidative stability and resistance to deposit formation.
- Sulphur content below usual detection limits.

## Quality levels

- Complies with the IEC 60296:2012 norm on unused mineral insulating oils for transformers and switchgear. Inhibited.

## Technical characteristics

	UNIT	METHOD	LIMITS
Kinematic viscosity at 40 °C	cSt	ASTM D445	11.1
Kinematic viscosity at -30 °C	cSt	ASTM D445	477
Density at 20 °C	g/ml	ASTM D4052	0.820
Flash point	°C	ASTM D92	193
Freezing point	°C	ASTM D97	-65
Breakdown voltage, untreated	kV	UNE EN 60156	60
Dielectric loss factor at 90 °C	--	UNE EN 60247	0.0006
Oxidation, maximum sludge	% weight	IEC 61125C	< 0.01
Oxidation, dielectric loss factor 90 °C	--	IEC 61125C	0.0010
Oxidation, total acidity	mg KOH/g	IEC 61125C	0.18

*The above mentioned characteristics are typical values and should not be considered product specifications.*

**Caution:** Any type of contamination (humidity, particles, etc.) can negatively affect the properties of the product. Special attention must be paid to avoid polar contaminants.

A product safety sheet is available upon request.

repsol.com  
+34 901 111 999

Lubricants technical data sheet. Revision 2. March 2019.