

Description

The lubricants included in this range are manufactured using selected and carefully additivated bases to make them hydraulic oils for general use.

These oils are specially suitable for most hydraulic circuits, including those requiring special anti-wear protection, both in industry and motoring (dumpers, civil works machines, etc.), regardless of the type of pump with which they are equipped and pressures under which they work.

Properties

- Resistance to oxidation, ageing and sludge formation
- Low pour point.
- High viscosity index.
- Compatible with joints.
- Good anti-foam properties.
- Marked anti-wear properties
- Easy water separation.

Quality levels

- DIN-51524 Part 2 HLP
- ISO 6743/4 HM
- ISO 11158
- AFNOR NF E 48-603 HL, HM.
- FILTERABILITY TEST AFNOR NF E 48-690 and 48-691.

Technical specifications

	UNIT	METHOD	VALUE					
ISO Grade			22	32	46	68	100	150
Viscosity at 100 °C	cSt	ASTM D 445	4.3	5.4	6.7	8.6	11.1	14.5
Viscosity at 40 °C	cSt	ASTM D 445	22	32	46	68	100	150
Viscosity index		ASTM D 2270	103	104	97	97	97	96
Density at 15 °C	g/cm ³	ASTM D 4052	0.865	0.878	0.876	0.882	0.887	0.893
Flash point	°C	ASTM D 92	200	215	220	230	245	250
Pour point	°C	ASTM D 97	-24	-24	-24	-24	-21	-21
FZG, damage stage		DIN 51354	--	11	11	11	11	11
4B wear, scar diameter	mm	ASTM D 4172	0.50	0.50	0.45	0.45	0.45	0.45
Res. Oxidation, acid number at 1500 hrs	mgKOH/g	ASTM D 943	<2	<2	<2	<2	<2	<2
De-emulsification ⁽¹⁾ 54°C/ ⁽²⁾ 82 °C)	min	ASTM D 1401	<20 ⁽¹⁾	<20 ⁽¹⁾	<20 ⁽¹⁾	<30 ⁽¹⁾	<30 ⁽²⁾	<30 ⁽²⁾
Copper corrosion 3 h at 100 °C		ASTM D 130	1b	1b	1b	1b	1b	1b

A safety data sheet is available on request.

repsol.com
+34 901 111 999

Technical data sheet for Lubricants. Revision 6. October 2013